

Compound Technical Data Sheet

Material : PEROXIDE CURED SILICONE

COMPOUND NUMBER : CMD-1026

COLOR : TRANSLUCENT

TEMPERATURE RANGE : -60 °C / + 180°C

<u>Original Physical Properties</u>	<u>Requirements</u>	<u>Results</u>
Hardness, (Shore A) (ASTM D2240)	80±5	82
Tensile Strength, (MPa) (ASTM D412-C)	6,00 (min)	6,16
Elongation, (%) (ASTM D412-C)	150(min)	166
Specific Gravity (g/cm ³)		1,232
Compression set, 22 Hrs @ 175°C (ASTM D395-B)		12,3

PRODUCT SPECIFICS

Odor : None

Storage Stability : 10 years

Meets : FDA CFR 177.2600

Meets : USP 30 Class VI-50°C <88>

Meets: USP 39 Cytotoxicity testing <87>

Meets : EC1935/2004 for Water & Acid & Ethanol only

Conform ADIF (Animal Derived Ingredient Free) BSE/TSE



GENERAL ADVICE

SIP : very good

CIP : very good

Mineral Oils & Fat : bad

WFI : good

Sterilization : excellent

Steam Sterilization : excellent

Silicone is porous and will absorb some of the active media that passes the surface.



This information is accurate to the best of our knowledge. We advice the users of our products to perform their own testing for chemical resistance and suitability of the particular applications.

Rev. date 11-2019