

Compound Data Sheet

Compound number	CMD-1015
Material	Peroxide Cured Silicone
Colour	Red/Brown
Odour	None
Temperature range	-60°C – +200°C
Storage Stability	10 years

Property (Norm)	Requirements	Results
Hardness [shore A] ASTM D2240-04	70±5	71
Tensile Strength [MPa] ASTM D412-06	5 (min)	6.5
Elongation [%] ASTM D412-06	150 (min)	273
Compression set [%] 22 Hrs @ 175°C ASTM D395-03B	25 plied (max)	24.1
Tear Strength [N/mm] ASTM D624-B	5 (min)	12.3
Density [g/cm³]		1.35

Meets

FDA	CFR 177.2600
Cytotoxicity <i>in vitro</i>	USP 35 <87>
Cytotoxicity <i>in vivo</i>	USP 35 <88> Class VI [121°C]
Migration (food)	EC1935/2004 for water and acid only
Conform	Animal Derived Ingredient Free (ADIF) & BSE/TSE free

General Advice

SIP	Very Good
CIP	Very Good
Mineral Oils & Fat	Poor
WFI	Good
Sterilization	Excellent
Steam Sterilization	Excellent

Silicone is porous and will absorb some of the media that passed the surface.

This information is accurate to the best of our knowledge. We advise the users of our products to perform their own testing for chemical compatibility and suitability for particular applications.