



Compound Data Sheet

Compound number	CMD-1084
Material	Platinum Cured Silicone
Compound	Wacker Elastosil® LR 3003/80 A/B + 1% ^m / _m TiO ₂
Colour	White
Odour	None
Temperature range	-60°C – +200°C
Storage Stability	10 years

Property (Norm)	Requirements	Results
Hardness [shore A] ISO 7619-1	75±5	76
Tensile Strength [N/mm ²] ISO 37 Type 1	7 (min)	8.2
Elongation % ISO 37 Type 1	200 (min)	268
Tear Strength [N/mm] ASTM D624-B	10.0 (min)	12.0
Density [g/cm ³]		1.15

Meets

FDA	CFR 177.2600
Cytotoxicity <i>in vitro</i>	USP 42 <87>
<i>Cytotoxicity in vivo</i>	
Physicochemical	USP <383> Opt. 2
Extractables	USP <665>
<i>Migration (food)</i>	
Conform	Animal Derived Ingredient Free (ADIF) & BSE/TSE free

General Advice

SIP	Very Good
CIP	Very Good
Mineral Oils & Fat	Poor
WFI	Good
Sterilization	Excellent
Steam Sterilization	Good

Silicone is porous and will absorb some of the media that passed the surface.

This information is accurate to the best of our knowledge. We advise the users of our products to perform their own testing for chemical compatibility and suitability for particular applications.